

iQ TORO SC

technical data

CERTIFICATION & CLASSIFICATION	STANDARDS	iQ Toro SC
Type of floor covering	ISO 10581	Permanently static conductive pressed homogeneous vinyl flooring
Binder content	ISO 10581	Type I
CE certification	EN 14041	Yes
Classification	ISO 10874	Commercial: 34 Industrial: 43

TECHNICAL CHARACTERISTICS	STANDARDS	iQ Toro SC
Wear layer thickness	ISO 24340	2.0 mm
iQ PUR		Yes
Total thickness	ISO 24346	2.0 mm
Total weight/m²	ISO 23997	2950 g
Form of delivery	ISO 24341 Sheet (rolls)	Approx. 23 l m x 200 cm Art. no. 3093 _ _ _ 3 digit colour number
	ISO 24342 Tiles (box)	61 x 61 cm 14 tiles/box = 5.21 m² Art. no. 3094 _ _ _ 3 digit colour number


TECHNICAL PERFORMANCES	STANDARDS	iQ Toro SC
Dimensional stability	ISO 23999	≤ 0.40% for rolls ≤ 0.25% for tiles
Reaction to fire	EN ISO 13501-1 EN ISO 9239-1 EN ISO 11925-2	Class B _{s1} ≥ 8 kW/m Pass
Residual indentation	ISO 24343-1	Required value: ≤ 0.10 mm Best measured value: 0.02 mm
Castors chair test	ISO 4918	Suitable
Static electrical discharge	EN 1815	< 2 kV
Electrical insulation	VDE 0100, Part 600	R _s ≤ 5 x 10 ⁹ Ohms
Electrical resistance	ESD-approval SP-method 2472 EN 1081	R _s ≤ 10 ⁹ Ohms R ₁ 5x10 ⁹ ≤ R _s ≤ 10 ¹⁰ Ohms R ₂ 5x10 ⁹ ≤ R _s ≤ 10 ¹⁰ Ohms R ₃ 5x10 ⁹ ≤ R _s ≤ 10 ¹⁰ Ohms ≤ 3.5x10 ⁹ Ohms
Clean room test	ASTM F24 F51	Class A
Ease of decontamination	ISO 8690	Good
Total VOC emissions	AgBB/DIBt	≤ 10 µg/m³ (after 28 days)
Underfloor heating		Suitable - max. 27°C
Thermal resistance	EN 12667	Approx. 0.01 m² K/W
Light fastness	EN ISO 105-B02	≥ level 7
Chemical resistance	ISO 26987	Good resistance
Bacteria resistance	ISO 846:Part C	Does not favour growth
Slip resistance	DIN 51130 EN 13896	R9 ≥ 0.3
Seam strength	EN 684	Average value: ≥ 240 N/50 mm Individual values: ≥ 180 N/50 mm
Colours		14

The above information is subject to modification for the benefit of further improvement. (05/16).


CUSTOMS TARIFF : 482050000000F

Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for these instructions.

iQ Toro SC	NCS N°	Welding Rod No.	iQ Toro SC	NCS N°	Welding Rod No.	iQ Toro SC	NCS N°	Welding Rod No.	iQ Toro SC	NCS N°	Welding Rod No.
100	S 1002-Y50R	1287 322	104	S 1005-Y40R	1288 255	572	S 1515-Y30R	1287 438	576	S 4020-G50Y	1287 309
101	S 2502-B	1291 811	105	S 2020-Y30R	1292 372	573	S 2030-Y30R	1287 059	578	S 6502-B	1291 216
102	S 4502-B	1292 383	107	S 2020-R90B	1291 210	574	S 4005-Y50R	1287 379			
103	S 8502-B	1292 384	570	S 1502-Y50R	1287 531	575	S 7005-Y80R	1287 456			



Logistics Information



General Information



According to European Classification ISO 10874 - EN 685

HK



■ **WESTERN EUROPE:** Austria: Tarkett Holding GmbH, Niederlassung Wien – Tel. +43 1 47 88 062 Belgium: Tarkett France Belux – Tel. +32 16 35 98 80 Denmark: Tarkett A/S – Tel. +45 43 90 60 11 Finland: Tarkett Oy – Tel. +358 9 4257 9000 France: Tarkett SAS – Tel. +33 1 41 20 42 49 Germany: Tarkett Holding GmbH, Bereich Objekt – Tel. +49 62 33 810 Greece: Tarkett Monoprosopi Ltd – Tel. +30 210 6745 340 Italy: Tarkett S.p.A. – Tel. +39 0744 7551 Luxembourg: Tarkett GDL SA – Tel. +352 949 211 8804 Netherlands: Tarkett Holding GmbH, Vestiging Nederland – Tel. +31 416 685 491 Norway: Tarkett AS – Tel. +47 32 20 92 00 Portugal: Tarkett SA – Tel. +351 21 427 64 20 Spain: Tarkett Floors S.L. – Tel. +34 91 358 00 35 Sweden: Tarkett Sverige AB – Tel. +46 771 25 19 00 Switzerland: Tarkett Holding GmbH, Bereich Objekt Schweiz – Tel. +41 043 233 7912 Turkey: Tarkett Aspen – Tel. +90 212 213 65 80 United Kingdom: Tarkett Ltd – Tel. +44 (0) 1622 854 040 **EASTERN EUROPE:** Baltic Countries: Tarkett Baltics: Tel. +370 37 262 220 Czech Republic: Tarkett France SAS, org. slozka – Tel. +420 271 001 602 Hungary: Tarkett Trade d.o.o. – Tel. +36 1 437 8150 Poland: Tarkett Polska Sp. z o.o. – Tel. +48 22 16 09 231 Russian Federation: ZAO Tarkett RUS – Tel. +7 495 775 3737 Slovakia: Tarkett France SAS, org. slozka – Tel. +421 248 291 317 South East Europe: Tarkett Trade d.o.o. – Tel. +381 21 7557 649 (44) 569 12 21 Ukraine: Tarkett UA – Tel. +38 (0) 44 569 12 21 **ASIA AND OCEANIA:** Australia: Tarkett Australia Pty Ltd – Tel. +61 2 88 53 12 00 China: Tarkett Floor Covering (Shanghai) Co. Ltd. – Tel. +86 (21) 60 95 68 38 ext 8011 North East Asia: Tarkett Hong Kong Limited – Tel. +852 2511 8711 India: Tarkett France (India Branch) – Tel. +91 11 4352 4073 South East Asia: Tarkett Flooring Singapore Pte. Ltd. – Tel. +65 6346 1585 **AFRICA:** Tarkett International: Tel. +33 1 41 20 41 01 **MIDDLE EAST:** Tarkett Middle East: Tel. +961 1 51 3363/4 **ISRAEL:** Tarkett International: Tel. +33 1 41 20 41 01 **NORTH AMERICA/USA:** Tarkett Inc. – Tel. +1 713 869 5811 / Johnsonite – Tel. +1 440 543 891 Canada: Tarkett Inc. – Tel. +1 450 293 173 **LATIN AMERICA:** Brazil: Tarkett – Tel. 55 12 3954 7108 Argentina – Chile – Uruguay: Tarkett Latam Mercosur – Tel. +54 11 47 08 07 72 / +54 9 11 44 46 88 88 Bolivia – Colombia – Ecuador – Panama – Paraguay – Peru – Trinidad and Tobago – Venezuela: Tarkett – Tel. +55 11 95494 0069 Mexico / Central America: Tarkett Latam Mexico – Tel. +55 11 98410 9310

WWW.MELAVINYL.COM

