

FICHA TÉCNICA - TOPFLOR

HOMOGÉNEOS - STANDARD

DESCRIPTION			
Total thickness	EN 428	mm	2.0mm
Wearlayer thickness	EN 429	mm	2.0mm
Weight	EN 430	g/m ²	3300g/m ²
Width	EN 426	cm	200cm
Length of sheet	EN 426	m	20m
CLASSIFICATION			
Classification	EN 685	class	34-43
Fire rating	NF P 92-506	--	M2
	EN 13 501-1	--	Class Bfl-S1
	DIN 4102	--	B1
	GB 8624-1997	--	GB 8624 B1
Toxic testing	GB 18586-2001	--	Pass
Electrical resistance	EN 1815	kv	< 2
	EN 1081	Ω	> 10 ⁹⁻¹⁰
Slip resistance dry	EN 13893	--	≥ 0.3
Slip resistance wet	DIN 51130	--	R9
PERFORMANCE			
Abrasion resistance	EN 649	--	Group M
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation	EN 433	mm	approx. 0.08
Thermal resistance	EN 12667	m ² K/W	≈ 0.01
Colour fastness	EN ISO 105-B02	degree	≥ 6
Chemical resistance	EN 423	--	good
Castor wheel test	EN 425	--	suitable
Impact sound reduction	EN ISO 717/2	dB	approx. +4
Flexibility	EN 435	--	excellent
Hygiene treatment	MRSA	--	very good
	EN ISO 846-A/C	--	Good
Surface treatment			PUR
Underfloor heating		°C	Suitable max. 28
Maritime usage	IMO RES A 653 (16)-IMO MSC 61 (67) ANNEX 1 PART 2.5		